



Technical Information of 4films fluffy digital

Version: 1.2
Language: en
Date: 10.07.2017

Description: One side soft coated film which is specially designed for all printed papers on common known digital printing methods.

Characteristic: Exceptional touch – excellent color clarity after lamination with excellent bonding strength to printed papers on common known digital printing methods



Properties	Test Method/Standard	Value	Unit
Thickness	DIN EN ISO 534	39	µm
Substance/Grammage	ISO 536	27,93	g/m ²
Yield	DIN 53375	46,08	m ² /kg
Tensile Strength at Break MD	-	-	N/mm ²
Tensile Strength at Break TD	-	-	N/mm ²
Elongation at Break MD	-	-	%
Elongation at Break TD	-	-	%
Gloss Angle of Incidence/Observation 60°/60°	ASTM D2457	7.5	GU
Haze	ASTM D1003	88,3	%
Surface Tension	DIN 55660-2	> 40	mN/m

Prior to each and any treatment or processing of the film, the customer is obliged to perform pre-tests under original production conditions in accordance with the form sheet Processing Recommendations. Damages resulting from the fact that the Customer did not or not properly carry out such mandatory pre-tests shall be borne by the Customer.

Explanation of Abbreviations:

ASTM	American Standard Test Method	GE	Gloss Units
DIN	Deutsche Industrie Norm [German Industry Norm]	JIS	Japanese Industrial Standard
DIN EN ISO	German, European and International Standard	MD	Main Direction
		TD	Transverse Direction

Processing Recommendations

4films fluffy digital

Prior to any treatment or processing of 4films-laminating films they must be tested in each case under the original conditions of production. Due to the great variety of processing machines and their adjustment parameters as well as the variety of materials on the market only recommendations are possible here.

4films fluffy digital lamination film can be processed with a Kalander temperature between 100°C and 120°C, but it is recommended to determine the appropriate Kalander temperature before use.

4films fluffy digital lamination film should have preferably a temperature less than 30 °C and humidity of 55 ± 5 % in storage areas. Storage at high temperatures or in a horizontal position should be avoided. The material should be consumed within three months of receipt.

To avoid damage or consequential costs, the customer has to ensure that when laminating with 4films-laminating films in the event of any defects in the film (eg wrinkling, stains, spots or other imperfections) the production has to be stopped immediately.

When using 4films-laminating films, it has to be verified throughout each job that a sufficient compound adhesion to the substrate to be laminated exists. In case of insufficient

compound adhesion, processing parameters such as pressure, machine speed and temperature should be varied.

In the case that the surface wettability of the substrate to be laminated is particularly poor, the customer might be required to improve the surface wettability beforehand, for instance, without limitation, by use of a corona treatment or to use another laminating procedure.

Prior to any treatment or processing of 4films-laminating film in following methods:

- .. UV varnishing
- .. hot foil stamping
- .. cold foiling
- .. adhesive bonding
- .. creasing
- .. grooving
- .. blind embossing
- .. die cutting
- .. pocket sealing
- .. pocket welding

it must take place before an suitability test to be used with the original materials under original conditions generally.

